

ARMOUR-SEAL™

Chassis Encapsulant

Application Tip Sheet

Apply only with Rhomar's **PISTOL-GRIP** Spray Gun

Always apply to a clean dry surface

Freezing: NEVER allow **ARMOUR-SEAL™** to freeze as this will render it permanently unusable

Do Not Apply to any exhaust systems

Before applying ARMOUR-SEAL shake each bottle vigorously by hand for 60 seconds

Before applying to oil pans and transmission pans reference OEM recommendations for external coatings

Applying to used vehicles:

Always clean rusted surfaces that have been exposed to road salts with Rhomar's **NEUTRO-WASH™** Salt & Chloride Neutralizer prior to applying **ARMOUR-SEAL™**

Applying to new vehicles

Apply 20-60 mils wet film thickness:

- 20 mils excellent for application over factory paint on undercarriage components
- 20-40 mils excellent for application over surface rust on undercarriage components
- 50-60 mils gives rust corrosion protection plus sound deadening
 - When you see sagging you are approximately 60 mils

Apply in temperatures above 50° F

Allow 24 hours dry time prior to road moisture exposure

Allow 72 hours for full cure

Clean **PISTOL-GRIP** Spray Gun and overspray with Rhomar's **RHOMA-SOL™** Emulsifier

Always clean **PISTOL-GRIP** Spray Gun after each usage

Use **ARMOUR-SEAL™** within 1 year of purchase date

ARMOUR-SEAL™ is designed to be a soft and flexible sacrificial protection to all chlorides when fully cured

CALL TOLL FREE TO REORDER



RHOMAR

solutions@rhomar.com
www.rhomar.com

2107 E Rockhurst St • Springfield, MO 65802

1-800-688-6221

417-866-5592