

BRIDGE-CON

Metal or Concrete Encapsulant

Description: **BRIDGE-CON** is specifically designed for encapsulating concrete or metal substructure components that are exposed to corrosive chlorides. **BRIDGE-CON** is also excellent for protecting metal, wood and concrete components of salt storage domes.

Application Method: Rhomar recommends applying **BRIDGE-CON** with the **BRIDGE-CON** Air Operated Spray Gun or by rolling with a thick nap roller. Apply product above 50°F.

Surface Preparation - Concrete: Always apply to a clean, dry surface, free of loose dirt and debris. Rhomar recommends applying **NEUTRO-WASH** Chloride Neutralizer to any surfaces that have been exposed to salt residue.

Surface Preparation - Metal: Rhomar suggests applying **BLACK-MAX** Cathodic Rust Arrestor, as a primer, to rusty metal components prior to application of **BRIDGE-CON**.

Coverage: **BRIDGE-CON** coverage is approximately 25-100 s.f. per gallon depending on porosity of substrate. Apply **BRIDGE-CON** to wet film thickness (WTF) of 15-20 mils.

Storage: Always store **BRIDGE-CON** at temperatures between 60°-110°F. Never allow product to freeze. Always keep **BRIDGE-CON** containers tightly sealed after usage, to prevent product from curing in container.

Clean-Up: When **BRIDGE-CON** is wet, you may clean tools and overspray with soap and water. When cured, remove with toluene or by sandblasting or with grinding wheel.

Safety: Always refer to **BRIDGE-CON** M.S.D.S.

For More Information Call: 1-800-688-6221

Marketed Exclusively By



RHOMAR

www.rhomar.com or e-mail solutions@rhomar.com
2107 E. Rockhurst Street
Springfield, MO 65802